

## Sealant Dichtfix

**Sprayable, MS polymer-based sealant for restoring the original texture following accident repair work.**

### Very broad adhesive range

Adheres to large range of surfaces, even without a primer coat.

### High Shore A hardness

The material is resistant to mechanical loads.

### High tensile strength and elongation at tear

The seam also withstands stronger movements/elongations.

### UV-stable

Excellent ageing behaviour, even when seams are not painted.

**“Wet on wet” can be painted over**

**Isocyanate- and silicone-free**



|                                  |   |
|----------------------------------|---|
| Contents                         | 310 ml  |
| Chemical basis                   | POP mixed polymer                                       |
| Density/conditions               | 1.48 g/cm <sup>3</sup> /at 23 °C, 50% relative humidity |
| Min./max. processing temperature | 5 to 30 °C  |
| Min./max. temperature resistance | -40 to 80 °C  |
| Shelf life from production       | 15 Month  |

| Colour | Art. no.        | P. Qty. |
|--------|-----------------|---------|
| Black  | <b>0893 226</b> | 1/12    |
| Grey   | <b>0893 228</b> | 1/12    |
| White  | <b>0893 227</b> | 1/12    |

## Details/Application

Seam sealing with replacement of parts in the engine compartment, boot, on the undercarriage, spring strut and wheel arches.



## Instructions

The base material must be clean, dry and free of grease. Dichtfix sealant is applied using a special pneumatic gun. The required textures and coat thicknesses are determined by the distance to the object or through the air pressure. For more information, please refer to the technical data sheet.

## Notice

Does not adhere to PP/PE/PTFE. Dichtfix must not come into contact with fresh (not cured) PU materials. When painting over with metallic paints, a blocking primer should definitely be applied. Due to the large number of paint systems, we recommend carrying out preliminary tests.

The usage instructions are recommendations based on the tests we have conducted and our experience; carry out your own tests before each application. Due to the large number of applications and storage and processing conditions, we do not assume any liability for a specific application result. Insofar as our free customer service provides technical information or acts as an advisory service, no responsibility is assumed by this service except where the advice or information given falls within the scope of our specified, contractually agreed service or the advisor was acting deliberately. We guarantee consistent quality of our products. We reserve the right to make technical changes and further develop products.

| Related products for | Designation  | Art. no.            |
|----------------------|--|---------------------|
| 0893 226             | Kombifix pneumatic cartridge gun For 310 ml cartridges | <b>0891 628 6</b>   |
|                      | Application nozzle for 310 ml plastic cartridges       | <b>0891 628 612</b> |
|                      | 2-component primer filler Multi-Fill                   | <b>0893 213 1</b>   |
| 0893 227             | Kombifix pneumatic cartridge gun For 310 ml cartridges | <b>0891 628 6</b>   |
|                      | Application nozzle for 310 ml plastic cartridges       | <b>0891 628 612</b> |
|                      | 2-component primer filler Multi-Fill                   | <b>0893 213 1</b>   |
| 0893 228             | Kombifix pneumatic cartridge gun For 310 ml cartridges | <b>0891 628 6</b>   |
|                      | Application nozzle for 310 ml plastic cartridges       | <b>0891 628 612</b> |
|                      | 2-component primer filler Multi-Fill                   | <b>0893 213 1</b>   |